

NATIONAL CERA LAB

CERAMIC LABORATORY

Shop No. 16, 17, Ground Floor, Dariyalal Plaza,
Nr. Argil Ceramic, 8-A, N/H, Morbi - 363 642 (Guj.) INDIA.

Ph. : 02822 244049, Mo. : 98252 62649, 96622 97005, 98257 99418
E-mail : nationalceralab@rediffmail.com

As per all Countries Export report of Wall, Floor, Vitrified Tiles & Sanitary Wares

Ref. No.

Date :

NCL/Glazed Vitrified/ISO/Stain/03/047/2022-2023

Issue Date- March. 01. 2023

Receive date of test sample :-

Feb. 27 . 2023

Issued To

Tile Merchant,
Dockrells Complex, Ballymount Rd Upper, Ballymount, Dublin 24
Rep. of Ireland

SAMPLE DESCRIPTION & NAME Glazed Vitrified Tiles size 1200x600 mm (Rectified) as submitted by the party.
Sample not drawn by National Cera Lab.

DESIGN LUNAR ASH

TEST REQUIRE AS PER AS PER ISO 13006:2018 Group B Ia

1 RESISTANCE TO STAIN	Stain put on tiles up to 24 hrs	Test Method	Require	Result
a Red Past in Light Oil (Fe2O3)	Stain remove by weak cleaning agent	ISO 10545 - 7	Class - 3, Min	Class - 4
b Green Past in Light Oil (Cr2O3)	Stain remove by hot water		Class - 3, Min	Class - 5
c Iodine in Alcohol 13g/l	Stain remove by hot water		Class - 3, Min	Class - 5
d Olive Oil	Stain remove by hot water		Class - 3, Min	Class - 5

Tested by



Aritra Bera (Lab Asst.)

Checked & Verified By



Nimesh Kavar (Testing Eng.)

Reviewed & Approved By



Jerambhai Kavar(QM/TM)