## **NATIONAL CERA LAB**

## **CERAMIC LABORATORY**

Shop No. 16, 17, Ground Floor, Dariyalal Plaza, Nr. Argil Ceramic, 8-A, N/H, Morbi - 363 642 (Guj.) INDIA. Ph.: 02822 244049, Mo.: 98252 62649, 96622 97005, 98257 99418

E-mail: nationalceralab@rediffmail.com

## As per all Countries Export report of Wall, Floor, Vitrified Tiles & Sanitary Wares

Receive date of test sample :- 12.07.2019

Ref. No.

Date:

NCL/Glazed Vitrified Tile /DIN/RAMP/07/026/2019-20 URL - TC626519000000409P

July. 14.2019

**Issued To** 

Tile Merchant. Dockrells Complex, Ballymount Rd Upper, Ballymount, Dublin 24 Rep. of Ireland

SAMPLE DESRIPTION & NAME

Outdoor Porcelain Tile/ Glazed Vitrified Tiles - size 900x600x20 mm Thickness

as submited by the party. Sample not drawn by National Cera Lab.

TEST DESIRED:

DIN EN Standard specification DIN EN: 14411: 2016 (Group Bla)

1 RAMP TEST

Party submitted sample size 900x500mm one number and 300x50 mm one of sample Tiles

## SLIP RESISTANCE TEST

Note

TEST METHOD BS EN 10545 - 17 : 2017 (Annex "C" & DIN 51130 : 2014 - 2 & DIN 51097 : 1992 - 11

STANDARD LIMIT		CORRECTED MEAN OVERALL	SLIP RESISTACE	
S-I	5.7° - 11.7°	ACCEPTANCE ANGLE	CLASS	
		6° UP TO 10°	R 9	
S-II	14.3° - 20.3°	OVER 10° UP TO 19°	R 10	
		OVER 19° UP TO 27°	R 11	
S-III	24.3° - 30.3°	OVER 27° UP TO 35°	R 12	
		OVER 35°	R 13	

Sr No	Sample Name	Measured Value	Average Value	Class	
1	900x600x20 mm Outdoor Porcelain Tiles	(1)24.7°,(2)25.0°,(3)25.2° (4)25.5°	25.1°	R11	

Authorised signaatory:

Name of signatory: J.M. Kavar ( Diploma in Ceramic Technology)

NATIONAL CERA

For

Designation of signatory:

National Cera LAB

